Milliken.

SOUTHERN ANALOG

Voltage

Modular Tile

Construction

Tufted, Textured Loop

Tile Size

50 cm x 50 cm (19.7" x 19.7")

Yarn Type

ECONYL® Solution-Dyed Nylon Type 6

Stain Resist / Soil Release

StainSmart®

Dye Method

Solution Dyed

Tufted Face Weight

 $15 \text{ oz/yd}^2 (508.6 \text{ g/m}^2)$

Gauge

1/12

Stitches Per Inch

10.4

Tufts

124/in² (1,920/100 cm²)

Finished Pile Height

0.13" (3.30 mm)

Finished Pile Thickness

0.092" (2.34 mm)

Average Density (Finished)

6,691

Standard Backing

PVC-Free WellBAC® Comfort Cushion

Available with TractionBack®

Recycled Content by Total Weight

Standard Backing: 47.8% Pre-Consumer, 8.2% Post-Consumer NSF 140 Platinum Backing Option: 36.8% Pre-Consumer, 19.2% Post-

Consumer

Embodied Carbon

 $7.57 (kg CO_{2}e)/m^{2}$

Nominal Total Thickness

0.31" (7.9 mm)

Nominal Total Weight

 $92.1 \text{ oz/yd}^2 (3,123 \text{ g/m}^2)$

Flammability (Radiant Panel

ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

 ≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20%

R.H.,70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Heavy Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care

Service Network

Indoor Air Quality—CRI Green Label

Plus™

GLP7205, Carpet Category 13X

Recommended Installation Method(s)

Monolithic (preferred), Ashlar,

Quarter-Turn

WARRANTIES

Lifetime Face Fiber Wear
Lifetime Antistatic
Lifetime Floor Compatibility
Lifetime Color Pattern Permanency
Lifetime Floor Release

Lifetime Cushion Resiliency
Lifetime Moisture Resistance
Lifetime Delamination of Backing
Lifetime Staining/Soiling (StainSmart®)
Lifetime Dimensional Stability

Lifetime Tuft Bind Lifetime Edge Ravel Flammability













This cushion-back carpet tile product is covered by one or more patents, published applications and/ or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.

